

DuPont™ Pyralux® AC

All-Polyimide Single-Sided Copper-Clad Laminate

Flexible Circuit Materials



Product Description

DuPont™ Pyralux® AC is a Single-sided Copper-clad Laminate featuring an adhesive-less, all-polyimide dielectric layer. This material exhibits excellent low loss performance and is ideal for use in single-side clad applications that require high density circuitry, along with chip-on-flex attachment. Offered with a variety of conductor types, DuPont™ Pyralux® AC provides designers, fabricators, and assemblers a versatile option to develop their flex circuit solution

Key Features and Benefits

- Low loss all-polyimide dielectric
- ED or RA Cu foil available with various surface treatments
- Excellent thermal resistance from all-polyimide dielectric
- Reliability during flex/bending enabled by excellent peel strength between dielectric and conductor
- Certified to IPC-4204/25
- UL 94V-0, UL File E161336
- RoHS Compliant

Packaging

DuPont™ Pyralux® AC Single-side Clad is supplied as 100 linear meter (328 ft) rolls in widths of either 250 mm (9.8 in) or 500 mm (19.7 in). Other sizes are available by special order.

Storage and Warranty

DuPont™ Pyralux® AC Single-side Clad should be stored in original packaging at temperatures of 4 - 29 °C (40 - 85 °F) and below 70% relative humidity. The product should not be frozen and should be kept dry, clean, and well-protected. Subject to compliance with the foregoing handling and storage recommendations, DuPont's warranties shall remain in effect for the period provided in the DuPont Standard Conditions of Sale.

Safe Handling

Prior to handling, DuPont recommends referencing the Pyralux® Safe Handling Guide available at pyralux.dupont.com.

Table 1 –Pyralux® AC Construction Options

Laminate Component		
Copper Foil		
Thickness, μm (oz/ft ²)	9 (0.25) 12 (0.33)	18(0.5) 35 (1.0)
Copper Foil Type	Rolled-Annealed (RA) Electro-Deposited (ED)	
Dielectric		
Thickness, μm (mil)	12 (0.5) 25 (1.0)	20 (0.8) 45 (1.8)

Table 2 –Pyralux® AC Single Side Clad Offerings

Product Code	Copper Thickness μm (oz/ft ²) & Type	Dielectric Thickness μm (mil)
AC091200EN	09 (0.25) ED	12 (0.5)
AC092500EN	09 (0.25) ED	25 (1.0)
AC121200EM	12 (0.33) ED	12 (0.5)
AC121200RY	12 (0.33) RA	12 (0.5)
AC182500EM	18 (0.5) ED	25 (1.0)
AC182500RY	18 (0.5) RA	25 (1.0)
AC352500RHV	35 (1.0) RA	25 (1.0)
AC354500EY	35 (1.0) ED	45 (1.8)

Pyralux® AC Construction Selection

A variety of Pyralux® AC Single-side Clad constructions, are commercially available. For help beyond the standard offerings in Table 2, please use the Laminate Product Selector at pyralux.dupont.com to identify the appropriate product code for your copper-clad laminate solution.



Processing

DuPont™ Pyralux® AC Single-side Clad is fully compatible with all conventional flexible circuit fabrication processes, including oxide treatment and wet chemical plated-through-hole de-smearing. Fabricated circuits can be cover-coated and laminated together to form multilayers or bonded to heat sinks using polyimide, acrylic, or epoxy adhesives. Pyralux® AC processing guide available from your DuPont sales representative.

Product Performance

Table 3 - DuPont™ Pyralux® AC Single-side Clad Properties

Property	Typical Values AC182500RY	Test Method
Dielectric Constant (Dk)		
1 MHz	3.7	IPC-TM-650 2.5.5.3
10 GHz	3.4	ASTM D2520
Loss Tangent (Df)		
1 MHz	0.003	IPC-TM-650 2.5.5.3
10 GHz	0.005	ASTM D2520
Adhesion to Copper (Peel Strength)		
As Received, N/mm (lb/in)	1.2 (6 - 7)	IPC-TM-650 2.4.9
After Solder, N/mm (lb/in)	1.2 (6 - 7)	
Dimensional Stability (MD/TD)		
After Etching, %	± 0.02 %	DuPont Method, TMA
After Thermal (200 °C for 30 min), %	± 0.04 %	
Coefficient of Thermal Expansion		
XY-Axis, ppm/°C	19	IPC-TM-650 2.4.41
Solder Float, 288 °C for 10 s	Pass	IPC-TM-650 2.4.13
Moisture Absorption, %	0.9	IPC-TM-650 2.6.2
Volume Resistivity, Ω·cm	> 10 ¹⁶	IPC-TM-650 2.5.17
Surface Resistance, Ω	> 10 ¹²	IPC-TM-650 2.5.17
Tensile Modulus, GPa	> 7.5	IPC-TM-650 2.4.19
Tensile Strength, MPa	> 190	IPC-TM-650 2.4.19
Elongation, %	21	IPC-TM-650 2.4.19
Flexural Endurance, cycles	> 60	JIS C6471 (MIT)
Glass Transition Temperature (Tg), °C	280	DuPont Method, TMA

Data within this table are typical values for the listed product. Performance can vary depending on construction and processing.

Quality and Traceability

DuPont™ Pyralux® AC Single-side Clad is manufactured under a certified ISO9001:2015 Quality Management System facility. Complete material and manufacturing records, which include archive samples of finished product, are maintained by DuPont. Each manufactured lot is identified for reference traceability. The packaging label serves as the primary tracking mechanism in the event of customer inquiry and includes the product name, batch number, size, and quantity.



pyralux.dupont.com

For more information on Pyralux® AC Single-side Clad or other DuPont products, please visit electronics.dupont.com.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. **CAUTION:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. © 2019 DuPont de Nemours, Inc. All rights reserved.